

## NON-SLIP TAPE

*Specialists in  
Safety  
Identification  
Products*

**Harris West**

5181 Argosy Avenue  
Huntington Beach, CA 92649

Phone:  
(714) 898-8048  
(800) 222-6866

Fax:  
(714) 898-7108  
(800) 228-1274

**Harris East**

181 Conant Drive  
Pawtucket, RI 02860

Phone:  
(401) 727-3160  
(800) 443-2821

Fax:  
(401) 727-3162

### COEFFICIENT OF FRICTION:

- Static Coefficient of Friction on wet surface: 1.06
- Static Coefficient of Friction on dry surface: 1.24
- Coefficient of friction tests run per specification Mil-D 17915C (ships) using rubber test vehicle. Higher numbers indicate better coefficient of friction

### GENERAL PROPERTIES:

- **ALUMINUM OXIDE 80-GRIT**
- **FLEXURE:** Bends over sharp 90 degree angles without fracture; after application to substrate, resists repeated bending without cracking or failure of bond.
- **TEMPERATURE LIMITS:** Has a useful temperature range of 40° F to 220° F. However, limited exposure to temperatures above 220° F will not harm the product.
- **STEAM CLEANING:** Applied product will tolerate steam cleaning.
- **DETERGENT CLEANING:** Applied product will tolerate detergent cleaning.
- **ENVIRONMENTAL RESISTANCE:** Product is essentially unaffected by climatic exposure and mild acid or alkali exposure under normal conditions.
- **SHELF LIFE:** Two years minimum.

### IMMERSION TEST DATA:

- **DETERGENT OR TAP WATER:** Properly installed, product can be used for over 168 hours of submersion. In continuously wet or submersed use, seal all exposed edges with our Edge Sealing compound.
- **CHLORINE (SWIMMING POOL) WATER:** Properly installed, product can be used for over 912 hours of total submersion in 0.6 to 6.0 PPM chlorine residual swimming pool water. For longer product use under these conditions, use our Edge Sealing compound on all exposed edges.
- **DIESEL FUEL OIL:** Product can be used under conditions of diesel fuel oil spillage or splash-on. In addition, product can be submerged in diesel fuel oil for over 96 hours without failure of product or bond. To increase product life under these conditions, seal all exposed edges with Edge Sealing compound.
- **GASOLINE:** Product can be used under conditions of intermittent gasoline spillage or splash-on. Can be used up to 6 hours submersed in gasoline, or for over 48 hours in gasoline submersion by sealing all edges with Edge Sealing compound.
- **BRAKE FLUID:** Properly installed, product can be used under conditions of intermittent brake fluid spillage or splash-on. Product will resist up to 10 hours of brake fluid submersion. For longest product life, wipe off brake fluid spillage and use Edge Sealing compound.
- **MOTOR OIL:** Product can be used under conditions of motor oil spillage or splash-on. In addition, product will tolerate over 30 hours of submersion in motor oil.

### PRODUCT CONFORMANCE TO SPECIFICATIONS:

- Product meets or exceeds the following specifications: Mil-D-17951C (ships), Motor Vehicle Safety Standard No. 302, Walkway Matting, Nonslip Mil-W-5044C, Type IV.